

Test Report

No. SH8187821/TX

Date: Dec 29, 2008

Page 1 of 2

KING TECH INDUSTRY CORPORATION
4907 MORENA BLDG, SUITE 1407, SAN DIEGO, CALIFORNIA

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : One sample of woven polyester/ silicone impregnated cutting in navy blue for apparel

Style No. : TWB 260-57AASI

Manufacturer : SHANGHAI KING TECH INDUSTRY

Country of Destination : U.S.A.

Test Performed * : Selected test(s) as requested by applicant * * *

Sample Receiving Date : DEC. 18, 2008

Testing Period : DEC. 24, 2008 –DEC. 29, 2008

Test Result(s) : For further details, please refer to the following page(s).

Signed for and on behalf of
SGS-CSTC Ltd.



Dido Zhou (Account Executive)

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this test report is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.

Test Result**Color Fastness to Sea Water** (AATCC 106-2002)

Change in shade	4.5
Staining on multi-fiber stripe	
Acetate	4.0
Cotton	4-5
Nylon	4.0
Polyester	4-5
Acrylic	4-5
Wool	4-5

Color Fastness to Chlorinated Water (ISO 105 E03-1994; 50mg/l available chlorine)

Change in shade	4.0
-----------------	-----

Remarks: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

End of Report

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.